



TEST REPORT

LAB LOCATION:TURKEY
LAB NO. : (7212)229-0201 R
SERVICE TYPE: Regular
DATE IN: August 17th, 2012
DATE OUT: September 05th, 2012
REVISION DATE: September 06th, 2012

MATERIAL SUBMITTED : LAVA METAL DÖKÜM SAN.TIC A.Ş.
Organize San. Bölgesi 22.cadde No:3 Eskişehir
(Attn: İlhan Argın)

SUPPLIER REFERENCE : /

SAMPLE DESCRIPTION : Enameled Cast Iron Cooker/Black

SUMMARY OF TEST RESULTS

TEST REQUIRED	PASS	FAIL	
Sensory Test – two simulants (LFGB)	X		
Leachable Lead and Cadmium (84/500/EEC)	X		
Extractable Lead and Cadmium (FDA)	X		

Bureau Veritas Consumer Products Services Turkey
BV CPS Test Lab. Ltd. Sti.

Ayca Cevikus
Customer Service Supervisor-Hardline

Elif Bozkurt
Team Leader - Analytical

Remark 1: Sensory Test was sub-contracted to BV- Germany in this report.

Revision Reason: As per applicant's request leachable cobalt testing result has been discarded from the report no 7212229-0201 dated September 05th, 2012

EXECUTIVE SUMMARY:

As per customer's request, submitted samples have been tested for the Sensory Analysis, Leachable Lead and Cadmium, and Extractable Lead and Cadmium according to the requirements of LFGB, 84/500/EEC and FDA. The Samples are rated as "PASS". Please see enclosed test results.

C/N NY/AC

PAGE 1 OF 8

BV CPS TEST LABORATUVARLARI LTD. STI.
BUREAU VERITAS CONSUMER PRODUCTS SERVICES
Mahmutbey Mahallesi, Hacı Bostan Caddesi, No: 4
K:4 34218 Bağcılar, İstanbul / Turkey
Tel:+90.212.494 35 35 Fax:+90.212.494 35 60
email:info.turkey@bvcp.com.tr
website: www.bureauveritas.com/cps

Remark: The tests which can not be performed in Turkey were sub-contracted to BV CPS Germany for those results in this report.

This report is governed by, and incorporates by reference, the Conditions of Testing as posted at the date of issuance of this report at www.bureauveritas.com/cps and is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our written permission. This report sets forth our findings solely with respect to the test samples identified herein. The results set forth in this report are not indicative or representative of the quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted. Our report includes all the tests requested by you and the results thereof based upon the information that you provided to us. You have 60 days from the date of issuance of this report to notify us of any material error or omission caused by our negligence, provided, however, that such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.

-SUBMITTED SAMPLES-



Sample Description Assigned by Laboratory:

Test Item	Description	Client Claimed Material
1	Enameled Cast Iron Cooker/Black	Enameled Cast Iron



TEST RESULTS

Sensory Test per LFGB –Change of Odour (Fatty food-Aqueous)-Butter: DIN 10955

Test condition: 24 hrs @ room temperature

Parameter	Unit	Result	Maximum Allowable Limit
		Item 1	
Sensory Test (grade)	-	0	≤ 2.5
Conclusion	-	PASS	-

Note: “ \leq ” = less than and equal

Ratings:

- 0= no observable deviation
- 1= minor deviation
- 2= small deviation
- 3= clear deviation
- 4= significant deviation

Method: Change of odour through direct contact, fatty food (aqueous)-butter DIN 10955

Sensory Test per LFGB –Change of Odour (Acidic and Aqueous food)- Still Water: DIN 10955

Test condition: 24 hrs @ room temperature

Parameter	Unit	Result	Maximum Allowable Limit
		Item 1	
Sensory Test (grade)	-	0	≤ 2.5
Conclusion	-	PASS	-

Note: “ \leq ” = less than and equal

Ratings:

- 0= no observable deviation
- 1= minor deviation
- 2= small deviation
- 3= clear deviation
- 4= significant deviation

Method: Change of odour through direct contact, Acidic and Aqueous food- Still Water: DIN 10955



TEST RESULTS

Sensory Test per LFGB –Change of Taste (Fatty food-Aqueous)-Butter: DIN 10955

Test condition: 24 hrs @ room temperature

Parameter	Unit	Result	Maximum Allowable Limit
		Item 1	
Sensory Test (grade)	-	0	≤ 2.5
Conclusion	-	PASS	-

Note: “ \leq ” = less than and equal

Ratings:

- 0= no observable deviation
- 1= minor deviation
- 2= small deviation
- 3= clear deviation
- 4= significant deviation

Method: Change of taste through direct contact, fatty food (aqueous)-butter DIN 10955

Sensory Test per LFGB –Change of Taste (Acidic and Aqueous food)- Still Water: DIN 10955

Test condition: 24 hrs @ room temperature

Parameter	Unit	Result	Maximum Allowable Limit
		Item 1	
Sensory Test (grade)	-	0	≤ 2.5
Conclusion	-	PASS	-

Note: “ \leq ” = less than and equal

Ratings:

- 0= no observable deviation
- 1= minor deviation
- 2= small deviation
- 3= clear deviation
- 4= significant deviation

Method: Change of taste through direct contact, Acidic and Aqueous food- Still Water: DIN 10955



TEST RESULTS

Leachable Lead and Cadmium –FDA Requirements

Test conditions: 4% acetic acid extraction at 20-24 °C for 24 hours

Parameter	Unit	Result	Maximum Allowable Limit
		Item 1	
Lead -Pb	ppm	< 0.05	1.0
Cadmium -Cd	ppm	<0.01	0.25
Conclusion	-	PASS	-

Note: < less than
ppm: parts per million

Method: 4% acetic acid extraction at 20-24 °C for 24 hours, determination with ICP-MS

Extractable Lead and Cadmium from Ceramicwares – 84/500/EEC & 2005/31/EC EN 1388-1 & 2: 1995

Test conditions: 4% acetic acid extraction at 20-24 °C for 24 hours

Parameter	Unit	Result	Maximum Allowable Limit
		Item 1	
Lead –Pb	ppm	< 0.05	1.0
Cadmium –Cd	ppm	<0.01	0.25
Conclusion	-	PASS	-

Note: < less than
ppm: parts per million

Method: 4% acetic acid extraction at 20-24 °C for 24 hours, determination with ICP-MS
Leaching volume of cookware: 1000 ml
Leaching volume of lid: 100 ml

APPENDIX



1. FDA Compliance Policy Guides - CPG 7117.06, CPG 7117.07, California Health and Safety Code 108860

Classification	Lead (ppm)	Cadmium (ppm)
Flatware (average of 6)	3.0	0.5
Small hollow ware (any one of 6)	2.0	0.5
Large hollow ware (any one of 6)	1.0	0.25
Cups & mugs (any one of 6)	0.5	0.5
Pitchers (any one of 6)	0.5	0.5/ 0.25*

*Remark: the limit of cadmium content of pitchers refers to large or small hollow ware depending on their capacity.

Initial Test (1 specimen)

Initial Test (1 specimen)						
Category	Classification basis	Lead	Cadmium	Cobalt (FOR German Standard Only)		Conclusion
1	Articles which cannot be filled or articles which can be filled with internal depth \leq 25 mm	$\leq 0.8 \text{ mg/dm}^2$	$\leq 0.07 \text{ mg/dm}^2$	Both ceramic and glass ware $\leq 0.1 \text{ mg/dm}^2$		Pass
		$> 1.2 \text{ mg/dm}^2$	$> 0.105 \text{ mg/dm}^2$	$> 0.15 \text{ mg/dm}^2$		Fail
		$0.8 < x \leq 1.2 \text{ mg/dm}^2$	$0.07 < x \leq 0.105 \text{ mg/dm}^2$	$0.1 < x \leq 0.15 \text{ mg/dm}^2$		Confirmation test is required
2	All other articles which can be filled	$\leq 4.0 \text{ mg/L}$	$\leq 0.3 \text{ mg/L}$	Ceramic ware $\leq 0.2 \text{ mg/L}$	Glass ware $\leq 0.01 \text{ mg/L}$	Pass
		$> 6.0 \text{ mg/L}$	$> 0.45 \text{ mg/L}$	$> 0.3 \text{ mg/L}$	$> 0.015 \text{ mg/L}$	Fail
		$4.0 < x \leq 6.0 \text{ mg/L}$	$0.3 < x \leq 0.45$	$0.2 < x$	$0.01 < x$	Confirmation test is
			mg/L	$\leq 0.3 \text{ mg/L}$	$\leq 0.015 \text{ mg/L}$	required
3	Cooking ware, packaging and storage vessels having a capacity of more than 3 litres	$\leq 1.5 \text{ mg/L}$	$\leq 0.1 \text{ mg/L}$	Both ceramic and glass ware $\leq 0.1 \text{ mg/L}$		Pass
		$> 2.25 \text{ mg/L}$	$> 0.15 \text{ mg/L}$	$> 0.15 \text{ mg/L}$		Fail
		$1.5 < x \leq 2.25 \text{ mg/L}$	$0.1 < x \leq 0.15 \text{ mg/L}$	$0.1 < x \leq 0.15 \text{ mg/L}$		Confirmation test is required



Confirmation Test (3 specimens)

Confirmation Test (3 specimens)						
Category	Classification basis	Lead	Cadmium	Cobalt (FOR Germany Standard Only)		Conclusion
1	Articles which cannot be filled or articles which can be filled with internal depth \leq 25 mm	\leq 0.8 mg/dm ² (average) and \leq 1.2 mg/dm ² (all)	\leq 0.07 mg/dm ² (average) and \leq 0.105 mg/dm ² (all)	Both ceramic and glass ware		Pass
		\leq 0.1 mg/dm ² (average) and \leq 0.15 mg/dm ² (all)				
		$>$ 0.8 mg/dm ² (average) and $>$ 1.2 mg/dm ² (anyone)	$>$ 0.07 mg/dm ² (average) and $>$ 0.105 mg/dm ² (anyone)	$>$ 0.1 mg/dm ² (average) and $>$ 0.15 mg/dm ² (anyone)		Fail
2	All other articles which can be filled	\leq 4.0 mg/L (average) and \leq 6.0 mg/L (all)	\leq 0.3 mg/L (average) and \leq 0.45 mg/L (all)	Ceramic ware	Glass ware	Pass
		\leq 0.2 mg/L (average) and \leq 0.3 mg/L (all)	\leq 0.01 mg/L (average) and \leq 0.015 mg/L (anyone)			
		$>$ 4.0 mg/L (average) and $>$ 6.0 mg/L (anyone)	$>$ 0.3 mg/L (average) and $>$ 0.45 mg/L (anyone)	$>$ 0.2 mg/L (average) and $>$ 0.3 mg/L (anyone)	$>$ 0.01 mg/L (average) and $>$ 0.015 mg/L (anyone)	Fail
3	Cooking ware, packaging and storage vessels having a capacity of more than 3 litres	\leq 1.5 mg/L (average) and \leq 2.25 mg/L (all)	\leq 0.1 mg/L (average) and \leq 0.15 mg/L (all)	Both ceramic and glass ware		Pass
		\leq 0.1 mg/L (average) and \leq 0.15 mg/L (all)				
		$>$ 1.5 mg/L (average) and $>$ 2.25 mg/L (anyone)	$>$ 0.1 mg/L (average) and $>$ 0.15 mg/L (anyone)	$>$ 0.1 mg/L (average) and $>$ 0.15 mg/L (anyone)		Fail